


WASHABLE BARRIER MASKS

Results – Comparative analysis



IR SST RECOMMENDATIONS

		61-940 (green)	61-941 (blue) 61-947 (black)	61-945 (green)	61-946 (blue)
SPRAYING	≥15/20	✓ 20/20	✓ 20/20	✓ 20/20	✓ 20/20
FILTRATION 	60% minimum	👍 50% minimum	✓ 65% minimum	👍 50% minimum	✓ 65% minimum
FILTRATION AT 0.3µm	Not specified	69.1%	77.9%	69.1%	77.9%
BREATHABILITY	<11 Pa·s/cm	✓ 6.14 Pa·s/cm**	✓ 8.58 Pa·s/cm*	✓ 6.14 Pa·s/cm**	✓ 8.58 Pa·s/cm**
BREATHABILITY*	<6.3 mmH ₂ O/cm ²	✓ 3.52 mmH ₂ O/cm ²	✓ 4.92 mmH ₂ O/cm ²	✓ 3.52 mmH ₂ O/cm ²	✓ 4.92 mmH ₂ O/cm ²

*The conversion factor is approximately 0.5736

**Converted

Key: Exceeds expectations ✓

Acceptable 👍